



MYREVEST
PURE ELEGANCE

MYPRIMER300

Aggregate primer for all types of surfaces.



Uses

As a primer based on acrylic resins in aqueous dispersion and inerts of siliceous nature, used as a bonding bridge between all types of surfaces and microcement.

Properties

- Provides a rough surface ensuring excellent adhesion on smooth or low absorption substrates.
- It is used for the application of all types of surfaces, plastering, tiling on concrete, ceramic, hydraulic tiles...
- Easy to apply, ready-to-use product.
- Water-based product, low VOC (volatile organic compounds), environmentally friendly.

Technical information

| Properties | Specification | Unit | Method |
|--------------------------------|--------------------------------|--------------------|-------------------------|
| Nature | Acrylic emulsion and aggregate | | |
| pH | 7,5-9 | | UNE-EN ISO 19396-1:2020 |
| Density | 1,50±0,05 | g/cm ³ | UNE-EN ISO 2811-1 |
| Viscosity at 23°C Comp. A | 5000±1000 | mPa-s | EN ISO 3219 |
| Non-volatile content | 61-63 | % | UNE-EN ISO 3251:2020 |
| Performance | 5-3 | m ² /Kg | |
| VOC:2024/42/IIA(g)(30)Max.VOCs | <1 | g/L | |
| Drying time to touch | 2-3 | hours | |

Application

The substrates must be clean and free of grease, oils, oxides, debris and loose or poorly adhered parts. Apply to the surface by brush or roller. Cover the entire surface, trying to apply a uniform film. The application temperature should be between 5-30° C. Wait approximately 2-3 hours (depending on the environmental conditions and the absorption of the substrate) to apply the microcement.

Special precautions

It is essential to follow the instructions on the label of the container. For further information, please refer to the product safety data sheet. Empty containers must be disposed of in accordance with current legislation.



C/ Cuenca 21-4-8,
46960 Valencia
(Spain)

T.617955352
info@myrevest.com info@
myrevest.com
www.myrevest.com

Cleaning of tools

The tools are washed with universal solvent immediately after use.

Presentation

It comes in 5 kg packages.

Storage conditions

The product should be stored in its original closed container and protected from the weather at temperatures between 10°C and 30°C, in a dry and well ventilated place, away from sources of heat and direct sunlight. The shelf life is 1 year from the date of manufacture, if stored properly.

The product must not be used for purposes other than those specified, without first having written instruction in its handling. It is always the responsibility of the user to take appropriate measures in order to comply with legislative requirements. The Safety Data Sheets of the product are available to the professional.

last edition: February 2025



**trademark
of quality
for professionals**